

ABSTRACT OF THE DISCLOSURE

5 A method of manufacturing a structure with pores
which are formed by anodic oxidation and whose layout,
pitch, position, direction, shape and the like can be
controlled. The method includes the steps of:
disposing a lamination film on a substrate, the
lamination film being made of insulating layers and a
layer to be anodically oxidized and containing aluminum
as a main composition; and performing anodic oxidation
10 starting from an end surface of the lamination film to
form a plurality of pores having an axis substantially
parallel to a surface of the substrate, wherein the
layer to be anodically oxidized is sandwiched between
the insulating layers, and a projected pattern
15 substantially parallel to the axis of the pore is
formed on at least one of the insulating layers at
positions between the pores.

RECEIVED 1989 09 10 10 10 10